Sunlord Business categorie	es: Level 0 (general o	confident	ial) Wire	Wound Chip	Ceramic Inducto	or Page 1 of ² Rev.(
SP	ECI	=	СА	. T I (ΟΝ	S	_
Customer							_
Product Name		Wir	e Wound	Chip Cer	amic Induc	tor	_
Sunlord Part Nur	nber		MWSD	1005C	T		_
Customer Part N	umber						
[⊠New Released, 【This SPEC is total 1 【ROHS Compliant Pa	4 pages includir	ng spec	ifications a		C No.: MW	SD0306220	0000
	Approved By	Che	cked By	Issued	1 Bv		
Shenzher Address: Sunlord Indust Tel: 0086-755-29832333	trial Park, Dafuyu	ian Indi		, Baoan, Sl		na 51811	-
[For Customer appro Qualification Status:	☐ Full		estricted	Date:	-		
Approved By	Verified B	у	Re-chec	жеа Ву	Checker	a By	
Comments:							

Page 2 of 14 Rev.03

【Version change history】

Rev.	Effective Date	Changed Contents	Change reasons	Approved By
01	1	New release	1	Qintian Hou

Caution

All products listed in this specification are developed, designed and intended for use in general electronics equipment. The products are not designed or warranted to meet the requirements of the applications listed below, whose performance and/or quality require especially high reliability, or whose failure, malfunction or trouble might directly cause damage to society, person, or property. Please understand that we are not responsible for any damage or liability caused by use of the products in any of the applications below. Please contact us for more details if you intend to use our products in the following applications.

- 1. Aircraft equipment
- 2. Aerospace equipment
- 3. Undersea equipment
- 4. nuclear control equipment
- 5. military equipment
- 6. Power plant equipment
- 7. Medical equipment
- 8. Transportation equipment (automobiles, trains, ships, etc.)
- 9. Traffic signal equipment
- 10. Disaster prevention / crime prevention equipment
- 11. Data-processing equipment
- 12. Applications of similar complexity or with reliability requirements comparable to the applications listed in the above

[Precautions]

- 1. Magnetic materials shall be far away from parts to avoid impacts on their electrical characteristics.
- 2. Parts could be damaged by external mechanical pressure or stacked heavy objects, as well as strong shaking & dropping.
- 3. Please do not store parts in bulk to prevent coils and parts being damaged.
- 4. Oversized external force to parts on PCB may lead to parts being damaged or slipped off.
- 5. Please do not use parts on edge or top of PCB board in your design to avoid parts being damaged during PCB is moved.
- 6. Please use flux contained with resin since the highly acidic (Chlorine content more than 0.2 wt%) or water-soluble one could damage the insulation film of wires, then causing short circuit of parts.
- 7. Please do not use the brush to clean product or its surroundings. If you use the brush to clean product or its surroundings on PCB,copper wire may be broke, causing the product open .



1. Scope

This specification applies to the MWSD1005C

2. Product Description and Identification (Part Number)

1) Description

Wire Wound Chip Ceramic Inductor, 1005, XXX nH± X% @XXXMHz, XXX Ω , XXX mA

2) Product Identification (Part Number)



① Type	
MWS	Wire Wound Chip Radio Frequency
101003	Inductor

③ Externa	al Dimensions [L X W] (mm)
1005	1.0 X 0.5

5 Nominal Inductance (nH)				
Example	Nominal Value			
1N0	1.0			
10N	10			
R10	100			

⑦ Packing	g
В	Bulk Package
Т	Tape & Reel

② Process	
D	Dip

④ Material Code				
Example	Nominal Value			
С	Ceramic			

6 Inducta	6 Inductance Tolerance					
В	±0.1nH					
С	±0.2nH					
S	±0.3nH					
D	±0.5nH					
G	±2%					
Н	±3%					
J	±5%					


3. Electrical Characteristics

Please refer to item5.

- 1) Operating and storage temperature range (individual chip without packing): -40 $^{\circ}$ C to +125 $^{\circ}$ C
- 2) Storage temperature range (packaging conditions): -10 $^\circ$ C ~+40 $^\circ$ C and RH 70% (Max.)

4. Shape and Dimensions


1) Dimensions: See the following.



Α.	В	С	D	E	HREF.	IREF.	JREF.	Unit: mm
1.1±0.1	0.6±0.1	0.55±0.1	0.5±0.1	0.2±0.1	0.65	0.35	0.50	

2) Electrode Coplanarity:0.1mm Max.

3) Structure: See the following.



No.	Components Material			
А	Coating	Ultraviolet epoxy resin		
В	Core	Ceramic		
C Wire		Polyurethane system enameled copper wire		
D	Electrodes	Mo-Mn with Ni and Sn plating		

5. Electrical Characteristics

I .MWSD1005C


Part Number	Inductance	Tolerance	Min. Quality Factor	L/Q Test Freq.	Max. DC Resistance	Max. Rated Current	Min. Self-resonant Frequency
Units	nH	-	-	MHz	Ω	mA	MHz
Symbol	L	-	Q	Freq.	DCR	lr	S.R.F
MWSD1005C0N8□T	0.8	B,C,S,D,K	14	250	0.035	1000	> 6000
MWSD1005C1N0□T	1.0	B,C,S,D,K	10	250	0.085	650	> 6000
MWSD1005C1N8□T	1.8	B,C,S,D,J, K	20	250	0.043	950	> 6000
MWSD1005C1N9□T	1.9	B,C,S,D,J, K	20	250	0.043	950	> 6000
MWSD1005C2N0 T	2.0	B,C,S,D,J, K	23	250	0.043	950	> 6000
MWSD1005C2N2□T	2.2	B,C,S,D,J, K,	22	250	0.058	820	> 6000
MWSD1005C2N4 T	2.4	B,C,S,D,J,K	18	250	0.091	650	>6000
MWSD1005C2N7 T	2.7	B,C,S,D,J,K	24	250	0.050	900	>6000
MWSD1005C3N0 T	3.0	S,D,K	24	250	0.063	790	> 6000
MWSD1005C3N3□T	3.3	B, C, S, D, J, K	24	250	0.063	790	> 6000
MWSD1005C3N6□T	3.6	B, C, S, D, J, K	24	250	0.063	790	> 6000
MWSD1005C3N9□T	3.9	B, C, S, D, J, K	24	250	0.063	790	> 6000
MWSD1005C4N1 T	4.1	B, C, S, D, J, K	22	250	0.070	700	> 6000
MWSD1005C4N3□T	4.3	B, C, S, D, J, K	22	250	0.070	750	> 6000
MWSD1005C4N7□T	4.7	B, C, S, D, J, K	20	250	0.120	570	> 6000
MWSD1005C5N1 T	5.1	B, C, S, D, J, K	23	250	0.100	620	> 6000
MWSD1005C5N6□T	5.6	B, C, S, D, J, K	25	250	0.078	710	> 6000
MWSD1005C5N8□T	5.8	B, C, S, D, J, K	25	250	0.078	710	> 6000
MWSD1005C6N2□T	6.2	B, C, S, D, J, K	25	250	0.078	710	> 6000
MWSD1005C6N8□T	6.8	G, H, J, K	24	250	0.105	610	6000
MWSD1005C7N5□T	7.5	G, H, J, K	25	250	0.12	570	6000
MWSD1005C8N2□T	8.2	G, H, J, K	25	250	0.11	590	5500
MWSD1005C8N7□T	8.7	G, H, J, K	25	250	0.11	590	5500
MWSD1005C9N0□T	9.0	G, H, J, K	25	250	0.11	590	5500
MWSD1005C9N1 T	9.1	G, H, J, K	25	250	0.11	590	5500
MWSD1005C10N□T	10	G, H, J, K	24	250	0.15	510	5500
MWSD1005C11N□T	11	G, H, J, K	26	250	0.12	570	5500
MWSD1005C12N□T	12	G, H, J, K	26	250	0.12	570	5500
MWSD1005C13N□T	13	G, H, J, K	24	250	0.18	460	5000
MWSD1005C14N□T	14	G, H, J, K	26	250	0.21	430	5000
MWSD1005C15N□T	15	G, H, J, K	26	250	0.21	430	5000
MWSD1005C16N□T	16	G, H, J, K	25	250	0.28	370	4500
MWSD1005C18N□T	18	G, H, J, K	25	250	0.28	370	4500
MWSD1005C19N□T	19	G, H, J, K	26	250	0.24	400	4000
MWSD1005C20N□T	20	G, H, J, K	26	250	0.24	400	4000
MWSD1005C22N□T	22	G, H, J, K	25	250	0.36	330	4000

Wire Wound Chip Ceramic Inductor Page 6

Page 6 of 14 Rev.03


							Rev.03
MWSD1005C23N□T	23	G, H, J, K	25	250	0.36	330	3800
MWSD1005C24N□T	24	G, H, J, K	25	250	0.36	330	3500
Part Number	Inductance	Tolerance	Min. Quality Factor	L/Q Test Freq.	Max. DC Resistance	Max. Rated Current	Min. Self-resonant Frequency
Units	nH	-	-	MHz	Ω	mA	MHz
Symbol	L	-	Q	Freq.	DCR	lr	S.R.F
MWSD1005C27N□T	27	G, H, J, K	25	250	0.38	320	3500
MWSD1005C30N□T	30	G, H, J, K	25	250	0.38	320	3300
MWSD1005C33N□T	33	G, H, J, K	24	250	0.55	260	3200
MWSD1005C36N□T	36	G, H, J, K	25	250	0.60	250	3100
MWSD1005C38N□T	38	G, H, J, K	25	250	0.60	250	3000
MWSD1005C39N□T	39	G, H, J, K	25	250	0.60	250	3000
MWSD1005C43N□T	43	G, H, J, K	25	250	0.68	240	3000
MWSD1005C47N□T	47	G, H, J, K	25	250	0.95	200	2900
MWSD1005C51N□T	51	G, H, J, K	25	250	0.95	200	2850
MWSD1005C56N□T	56	G, H, J, K	25	250	1.05	190	2800
MWSD1005C62N□T	62	G, H, J, K	25	250	1.05	190	2600
MWSD1005C68N□T	68	G, H, J, K	25	250	1.35	170	2500
MWSD1005C75N□T	75	G, H, J, K	24	250	1.75	140	2400
MWSD1005C82N□T	82	G, H, J, K	25	250	1.90	140	2300
MWSD1005C91N□T	91	G, H, J, K	25	250	1.95	140	2100
MWSD1005C96N□T	96	G, H, J, K	24	250	2.06	130	1500
MWSD1005CR10□T	100	G, H, J, K	24	250	2.06	130	1500
MWSD1005CR11□T	110	G, H, J, K	25	250	2.38	120	1200
MWSD1005CR12□T	120	J, K	25	250	2.66	110	1000
MWSD1005CR27□T	270	J, K	10	100	3.30	100	400

II. Typical Electrical Characteristics



Inductance vs. Frequency Characteristics

Q vs. Frequency Characteristics



6. Test and Measurement Procedures

6.1 Test Conditions

Unless otherwise specified, the standard atmospheric conditions for measurement/test as:

- a. Ambient Temperature: 20±15°C
- b. Relative Humidity: 65%±20%
- c. Air Pressure: 86 KPa to 106 KPa

If any doubt on the results, measurements/tests should be made within the following limits:

- a. Ambient Temperature: 20±2°C
- b. Relative Humidity: 65%±5%
- c. Air Pressure: 86KPa to 106 KPa


6.2 Visual Examination

a. Inspection Equipment: 30X magnifier

6.3 Electrical Test

- 6.3.1 DC Resistance (DCR)
 - a. Refer to Item 5.

- b. Test equipment: HIOKI3540 or equivalent.
- 6.3.2 Inductance (L)
 - Refer to Item 5. a.
 - Test equipment: Agilent4287A+Agilent16197A or equivalent. b.
 - Test signal: -13dBm or 10mA c.
 - Test frequency refers to Item 5 d.
- 6.3.3 Q Factor (Q)
 - Refer to Item 5. a.
 - b. Test equipment: Agilent4287A+Agilent16197A or equivalent.
 - c. Test signal: -13dBm or 10mA
 - d. Test frequency refers to Item 5.
- 6.3.4 Self-Resonant Frequency (SRF)
 - Refer to Item 5. a.
 - b. Test equipment: Agilent E4991A+Agilent16197A and HP 8753E or equivalent.
 - c. Test signal: -20dBm or 50mV
- 6.3.5 Rated Current
 - a. Refer to Item 5.
 - b. Test equipment (see Fig.6.3.5-1): Electric Power, Electric current meter, Thermometer.
 - Measurement method (see Fig. 6.3.5-1): C.
 - 1. Set test current to be 0 mA.
 - 2. Measure initial temperature of chip surface.
 - Gradually increase voltage and measure chip temperature for corresponding current. 3.
 - d. Definition of Rated Current (Ir): Ir is direct electric current as chip surface temperature rose just 20°C against chip initial surface temperature (Ta) (see Fig. 6.3.5-2).



Page 8 of 14 Rev.03

6.4 Reliability Test

Items	Requirements	Test Methods and Remarks
6.4.1 Terminal Strength	No removal or split of the termination or other defects shall occur. Chip Chip Pad Glass Epoxy Board	 Solder the inductor to the testing jig (glass epoxy board) using eutectic solder. Then apply a force in the direction of the arrow. 4N force. Keep time: 10±1s Speed: 1.0 mm/s.
6.4.2 Resistance to Flexure	No visible mechanical damage.	 Solder the inductor to the test jig. Using a eutectic solder. Then apply a force in the direction shown as left. Flexure: 2mm Pressurizing Speed: 0.5mm/sec. Keep time: 5sec.
6.4.3 Vibration 6.4.4 Dropping	 No visible mechanical damage. Inductance change: within ±5% Q factor change: within ±20% Cu pad Solder mask Cu pad For the solder mask Glass Epoxy Board 	 Solder the inductor to the testing jig (glass epoxy board) using eutectic solder. The inductor shall be subjected to a simple harmonic motion having total amplitude of 1.5mm, the frequency being varied uniformly between the approximate limits of 10 and 55 Hz. The frequency range from 10 to 55 Hz and return to 10 Hz shall be traversed in approximately 1 minute. This motion shall be applied for a period of 2 hours in each 3 mutually perpendicular directions (total of 6 hours) Drop chip inductor 10 times on a concrete floor from a
0.4.4 Dropping	 No visible mechanical damage. Inductance change: within ±5% Q factor change: within ±20% 	height of 100 cm.
6.4.5 Temperature coefficient	+50±100ppm/℃	 Between -40℃ and +125℃ With a reference value of +20℃
6.4.6 Solderability	90% or more of electrode area shall be Coated by new solder.	 Electrode of the coil shall be immersed in flux for 5 to 10 Seconds. The coil shall be immersed in solder bath at a temperature of 240±5°C, Duration for 3±0.5 seconds. Solder: Sn/3.0Ag/0.5Cu Flux: 25% Resin and 75% ethanol in weight.
6.4.7 Resistance to Soldering Heat	 No visible mechanical damage. Inductance change: within ±5% Q factor change: within ±20% 	Re-flowing Profile: 260°C Max Ramp Up Rate=3°C/sec. 217°C Max Ramp Down Rate =6°C/sec. 200°C 150°C 60~120sec. 25°C Time 25°C to Peak= 8 min Max

Sunlord Business categories: Level 0 (general confidential)

Ambient Temperature

1

2

3

6.4.8 Thermal

Shock

6.4.9

Low

Resistance to

Temperature

1

2

3

Wire Wound Chip Ceramic Inductor

categories. Lever o (general connuential)	Rev.03
No visible mechanical damage. Inductance change: within ±5% Q factor change: within ±20% +125°C 30 min. 30 min. pient	 Temperature, Time: -40°C for 30±3 min→+125°C for 30±3min Transforming interval: 20s (max.) Tested cycle: 100 cycles The chip shall be stabilized at normal condition for 1~2 hours before measuring.
No visible mechanical damage. Inductance change: within ±5% Q factor change: within ±20%	 Temperature: -40±2°C Duration: 1000⁺²⁴ hours The chip shall be stabilized at normal condition for 1~2 hours before measuring.
No mechanical damage. Inductance change: within ±5% Q factor change: within ±20%	 Temperature: 125±2℃ Duration: 1000⁺²⁴ hours The chip shall be stabilized at normal condition for 1~2 hours before measuring.
No mechanical damage.	 Temperature: 60±2℃, Humidity: 90% to 95% RH

6.4.10	1	No mechanical damage.	1	Temperature: 125±2°C
Resistance to	2	Inductance change: within ±5%	2	Duration: 1000 ⁺²⁴ hours
High	3	Q factor change: within ±20%	3	The chip shall be stabilized at normal condition for 1~2
Temperature				hours before measuring.
6.4.11	1	No mechanical damage.	1	Temperature: 60±2°C, Humidity: 90% to 95% RH
Damp Heat	2	Inductance change: within ±5%	2	Duration: 1000 ⁺²⁴ hours
(Steady	3	Q factor change: within ±20%	3	The chip shall be stabilized at normal condition for 1~2
States)				hours before measuring.
6.4.12	1	No mechanical damage.	1	Temperature: $60\pm2^\circ C$,Humidity: 90% to 95% RH
Loading Under	2	Inductance change: within ±5%	2	Duration: 1000 ⁺²⁴ hours
Damp Heat	3	Q factor change: within ±20%	3	Applied current: Rated current.
			4	The chip shall be stabilized at normal condition for 1~2
				hours before measuring.
6.4.13 Loading	1	No mechanical damage.	1	Temperature: 125±2°C
at High	2	Inductance change: within ±5%	2	Duration: 1000 ⁺²⁴ hours
Temperature	3	Q factor change: within ±20%	3	Applied current: Rated current.
(Life Test)			4	The chip shall be stabilized at normal condition for 1~2
				hours before measuring.

7. Packaging and Storage

7.1 Packaging

There is one type of packaging for the chip inductors. Please specify the packing code when ordering. Tape Carrier Packaging:


Packaging code: T

- Tape carrier packaging are specified in attached figure Fig.7.1-1~4 а.
- b. Tape carrier packaging quantity please see the following table:

Туре	1005			
Таре	Paper	Таре		
Quantity	Standard	10K		
Quantity	Minimum	5K		


Page 9 of 14

(1) Taping Drawings (Unit: mm)




Remark: The sprocket holes are to the right as the tape is pulled toward the user.

(2) Taping Dimensions (Unit: mm)





(3) Leader and blank portion












178±2

(5) Peeling off force: 10gf to 70gf in the direction show below.



7.2 Storage

- a. The solderability of the external electrode may be deteriorated if packages are stored where they are exposed to high humidity. Package must be stored at 40°C or less and 70% RH or less.
- b. The solderability of the external electrode may be deteriorated if packages are stored where they are exposed to dust of harmful gas (e.g. HCl, sulfurous gas of H₂S)
- c. Packaging material may be deformed if package are stored where they are exposed to heat of direct sunlight.
- d. Minimum packages, such as polyvinyl heat-seal packages shall not be opened until they are used. If opened, use the reels as soon as possible.
- e. Solderability shall be guaranteed for <u>12</u> months from the date of delivery on condition that they are stored at the environment specified in specification. For those parts, which passed more than <u>12</u> months shall be checked solder-ability before use.

8. Warning and Attentions


8.1 Precautions on Use

- a. Always wear static control bands to protect against ESD.
- b. Any devices used (soldering iron, measuring instruments) should be properly grounded.
- c. Use non-magnetic tweezers when handing the chips.
- d. Pre-heating when soldering, and refer to the recommended condition specified in specification.
- e. Don't apply current in excess of the rated current value. It may cause damage to components due to over-current.
- f. Keep clear of anything that may generate magnetic fields such as speakers, coils.
- g. When soldering, the electrical characteristics may be varied due to hot energy and mechanical stress.
- h. When coating products with resin, the relatively high resin curing stress may change the electrical characteristics. For exterior coating, select resin carefully so that electrical and mechanical performance of the product is not affected. Before using, please evaluate reliability with the product mounted in your application set.
- i. When mount chips with adhesive in preliminary assembly, do appropriate check before the soldering stage, i.e., the size of land pattern, type of adhesive, amount applied, hardening of the adhesive on proper usage and amounts of adhesive to use.
- j. Mounting density: Add special attention to radiating heat of products when mounting other components nearby. The excessive heat by other products may cause deterioration at joint of this product with substrate.
- k. Since some products are constructed like an open magnetic circuit, narrow spacing between components may cause magnetic coupling.
- I. Please do not give the product any excessive mechanical shocks in transportation.
- m. Please do not touch wires by sharp terminals such as tweezers to avoid causing any damage to wires.
- n. Please do not add any shock and power to the soldered product to avoid causing any damage to chip body.
- o. Please do not touch the electrodes by naked hand as the solderability of the external electrodes may deteriorate by grease or oil on the skin.


8.2 PCB Bending Design


The following shall be considered when designing and laying out PCB's.

a. PCB shall be designed so that products are not subjected to the mechanical stress from board warp or deflection.



Products shall be located in the sideways direction to the mechanical stress.





Product shall be located carefully because they may be subjected to the mechanical stress in order of A>C=B>D.

c. When splitting the PCB board, or insert (remove) connector, or fasten thread after mounting components, care is required so as not to give any stress of deflection or twisting to the board. Because mechanical force may cause deterioration of the bonding strength of electrode and solder, even crack of product body. Board separation should not be done manually, but by using appropriate devices.

8.3 Recommended PCB Design for SMT Land-Patterns

When chips are mounted on a PCB, the amount of solder used (size of fillet) and the size of PCB Land-Patterns can directly affect chip performance (such as Q). And they can also cause other soldering question (such as offset and side lap). Therefore, the following items must be carefully considered in the design of solder land patterns.

- a. Please use the PCB pad and solder paste we recommend, and contact us in advance if they need to be changed.
- b. Please use flux contained with resin since the highly acidic (Chlorine content more than 0.2 wt%) or water-soluble one could damage the insulation film of wires, then causing short circuit of parts.
- c. The amount of solder applied can affect the ability of chips to withstand mechanical stresses which may lead to breaking or cracking. Therefore, when designing land-patterns it is necessary to consider the appropriate size and configuration of the solder pads which in turn determines the amount of solder necessary to form the fillets.
- d. When more than one part is jointly soldered onto the same land or pad, the pad must be designed that each component's soldering point is separated by solder-resist.


Recommended land dimensions please refer to product specification.

9. Recommended Soldering Technologies

This product is only for reflow soldering and iron soldering.

9.1 Re-flowing Profile


- \triangle Preheat condition: 150~200 °C/60~120sec.
- \triangle Allowed time above 217C: 60~90sec.
- △ Max temp: 260°C
- \triangle Max time at max temp: 10sec.
- △ Solder paste: Sn/3.0Ag/0.5Cu
- △ Allowed Reflow time: 2 times max.



[Note: The reflow profile in the above table is only for qualification and is not meant to specify board assembly profiles. Actual board assembly profiles must be based on the customer's specific board design, solder paste and process, and should not exceed the parameters as the Reflow profile shows.]

9.2 Iron Soldering Profile

- △ Iron soldering power: 30W Max.
- \triangle Preheat condition: 150°C/60sec.
- △ Soldering tip temperature: 350°C Max.
- △ Soldering time: 3sec. Max.
- △ Solder paste: Sn/3.0Ag/0.5Cu
- \triangle Iron Soldering time: 1 time max.




[Note: Take care not to apply the tip of the soldering iron to the terminal electrodes.]

9.3 Maintenance of heat gun (for your reference)

- △ Power output: 30W
- △ Temperature: 350°C Max
- △ Heat time: More than 5 seconds heating may cause short circuit of parts.

10. Solder Volume

Solder shall be used not to exceed as shown below.



a. Accordingly increasing the solder volume, the mechanical stress to chip is also increased.Exceeding solder volume may cause the failure of mechanical or electrical performance.

Rev.03

- b. Before soldering, please ensure that the solder should not adhere to the wire part of chip.
- c. Please pay particular attention to whether there is flux remaining on surface of the wire part of chip after subjected to reflow soldering since this may causing short circuit of parts.

11. Cleaning

Products shall be cleaned on the following conditions:

- a. Cleaning temperature shall be limited to 60°C Max. (40°C Max. for fluoride and alcohol type cleaner.)
- b. Ultrasonic cleaning shall comply with the following conditions, avoiding the resonance phenomenon at the mounted products and PCB.

Power: 20W/I Max.

Frequency: 28 KHz to 40 KHz

- Time: 5 minutes Max
- c. Cleaner
 - i. Alternative cleaner
 - Isopropyl alcohol (IPA)
 - HCFC-225
 - ii. Aqueous agent
 - Surface Active Agent Type (Clean through-750H)
 - Hydrocarbon Type (Techno Cleaner-335)
 - Higher Alcohol Type (Pine Alpha ST-100S)
 - Alkali saponifier Type (% Aqua Cleaner 240)
 - X Alkali saponification shall be diluted to 20% volume with de-ionized water.
 - ※ Please contact our technical service department before using other cleaner.
- d. There shall be no residual flux and residual cleaner after cleaning. In the case of using aqueous agent, product shall be dried completely after rinse with de-ionized water in order to remove the cleaner.
- e. Some products may become slightly whitened. However, product performance or usage is not affected.
- f. Please take care of winding part while cleaning.
- g. After cleaning, parts could be subjected to the next reflow soldering till the solvent remaining on surface of parts being volatilized.

12. Others

- a. We will not inform you of the improvement on specification of parts in advance.
- b. We will not inform you of the change on specification of parts during design in advance.
- c. Please contact us for the date to realize mass production of parts being designed.

Page 14 of 14 Rev.03

	File No:	A			
Effective date:		Applied to Wire Wound Ceramic Inductor Series			
No.	Defect Item Item	Graphic Schematic Drawing	Rejection identification Criteria		
1	Wire off/ Welding Spot Off		The solder joint Welding Spot of wire break away fr electrodes, or over the electrodes.		
2	Solder misplace		Solder joints are not at electrode side but at the coar side or flank.		
3	Coating		Coating at flank		
3	misplace		Coating at electrodes side		